
USACE / NAVFAC / AFCEC

UFGS-32 12 15.13 (November 2020)

Change 1 - 05/22

Preparing Activity: USACE

Superseding

32 12 15.13 (November 2017)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated April 2024

SECTION TABLE OF CONTENTS

DIVISION 32 - EXTERIOR IMPROVEMENTS

SECTION 32 12 15.13

ASPHALT PAVING FOR AIRFIELDS

11/20, CHG 1: 05/22

PART 1 GENERAL

- 1.1 FULL PAYMENT
 - 1.1.1 Method of Measurement
 - 1.1.2 Basis of Payment
- 1.2 PERCENT PAYMENT
 - 1.2.1 Mat and Joint Densities
 - 1.2.2 Pay Factor Based on In-place Density
 - 1.2.3 Payment Adjustment for Smoothness (Final Wearing Surface Only)
 - 1.2.3.1 Longitudinal Smoothness
 - 1.2.4 Laboratory Air Voids and Theoretical Maximum Density
 - 1.2.4.1 Mean Absolute Deviation
 - 1.2.5 Pay Factor Based on Plan Grade
- 1.3 REFERENCES
- 1.4 AIRFIELD ASPHALT PAVING WORKSHOP
- 1.5 SUBMITTALS
- 1.6 CONTRACTOR QUALITY CONTROL STAFF
- 1.7 ACCEPTANCE
 - 1.7.1 Acceptability of Work
 - 1.7.2 Acceptance Requirements
 - 1.7.3 Pavement Lots
 - 1.7.4 Sublot Sampling
 - 1.7.5 Additional Sampling and Testing
 - 1.7.6 Theoretical Maximum Density (TMD)
 - 1.7.7 Laboratory Air Voids
 - 1.7.8 In-place Density
 - 1.7.9 Surface Smoothness
 - 1.7.9.1 Straightedge Testing
 - 1.7.9.2 Profilograph Testing
 - 1.7.9.3 Final Profilograph Testing
 - 1.7.10 Plan Grade
- 1.8 Laboratory Accreditation and Validation
- 1.9 ENVIRONMENTAL REQUIREMENTS

PART 2 PRODUCTS

- 2.1 SYSTEM DESCRIPTION
- 2.2 Equipment
 - 2.2.1 Asphalt Mixing Plant
 - 2.2.1.1 Truck Scales
 - 2.2.1.2 Inspection of Plant
 - 2.2.1.3 Storage Silos
 - 2.2.2 Hauling Equipment
 - 2.2.3 Material Transfer Vehicle (MTV)
 - 2.2.4 Asphalt Pavers
 - 2.2.4.1 Receiving Hopper
 - 2.2.4.2 Automatic Grade Controls
 - 2.2.5 Rollers
 - 2.2.6 Diamond Grinding
- 2.3 AGGREGATES
 - 2.3.1 Coarse Aggregate
 - 2.3.2 Fine Aggregate
 - 2.3.3 Mineral Filler
 - 2.3.4 Aggregate Gradation
- 2.4 ASPHALT BINDER
- 2.5 MIX DESIGN
 - 2.5.1 JMF Requirements
 - 2.5.2 Adjustments to JMF
- 2.6 RECLAIMED ASPHALT PAVEMENT
 - 2.6.1 RAP Mix
- 2.7 RECYCLED ASPHALT SHINGLES

PART 3 EXECUTION

- 3.1 CONTRACTOR QUALITY CONTROL
 - 3.1.1 General Quality Control Requirements
 - 3.1.2 Testing Laboratory
 - 3.1.3 Quality Control Testing
 - 3.1.3.1 Asphalt Content
 - 3.1.3.2 Aggregate Properties
 - 3.1.3.3 Temperatures
 - 3.1.3.4 Moisture Content of Aggregate
 - 3.1.3.5 Moisture Content of Mixture
 - 3.1.3.6 Laboratory Air Voids, TMD, VMA, Marshall Stability and Flow
 - 3.1.3.7 In-Place Density
 - 3.1.3.8 Grade and Smoothness
 - 3.1.3.9 Additional Testing
 - 3.1.3.10 QC Monitoring
 - 3.1.4 Sampling
 - 3.1.5 Control Charts
- 3.2 Government Quality Assurance (QA)
- 3.3 PREPARATION OF ASPHALT BINDER MATERIAL
- 3.4 PREPARATION OF MINERAL AGGREGATE
- 3.5 PREPARATION OF ASPHALT MIXTURE
- 3.6 PREPARATION OF THE UNDERLYING SURFACE
- 3.7 TEST SECTION
 - 3.7.1 Sampling and Testing for Test Section
 - 3.7.2 Additional Test Sections
- 3.8 TRANSPORTING AND PLACING
 - 3.8.1 Transporting
 - 3.8.2 Placing
- 3.9 COMPACTION OF MIXTURE
 - 3.9.1 General

- 3.9.2 Segregation
- 3.10 JOINTS
 - 3.10.1 Transverse Joints
 - 3.10.2 Longitudinal Joints
 - 3.10.3 Echelon Paving
 - 3.10.4 Asphalt Pavement-Portland Cement Concrete Joints

-- End of Section Table of Contents --

USACE / NAVFAC / AFCEC UFGS-32 12 15.13 (November 2020)
Change 1 - 05/22

Preparing Activity: USACE Superseding
32 12 15.13 (November 2017)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated April 2024

SECTION 32 12 15.13

ASPHALT PAVING FOR AIRFIELDS
11/20, CHG 1: 05/22

NOTE: This guide specification covers the requirements for bituminous intermediate and wearing courses (central-plant hot-mix and warm-mix) for airfields using Marshall or Gyratory compaction method.

Adhere to [UFC 1-300-02](#) Unified Facilities Guide Specifications (UFGS) Format Standard when editing this guide specification or preparing new project specification sections. Do not edit or rewrite the unbracketed text without the express consent of the Corps of Engineers Transportation Systems Center (TSMCX), the Air Force Civil Engineer Center (AFCEC) pavement subject matter expert (SME), or the Naval Facilities Engineering Systems Command (NAVFAC). Edit bracketed items by choosing applicable item(s) or inserting appropriate text.

Comments, suggestions and recommended changes for this guide specification are welcome and should be submitted as a [Criteria Change Request \(CCR\)](#).

PART 1 GENERAL

NOTE: Make modifications within bracketed items to this guide specification during conversion to a project specification in accordance with the NOTES which are located throughout the document. These NOTES are instructions to the designer, and will not appear in the project specification.

Edit specifications developed for Corps of Engineers managed projects in accordance with ER 1110-34-1 Engineering and Design Transportation Systems Mandatory Center of Expertise (Section 11, 12, App A, B, C).

This guide specification only pertains to the hot-mix and warm-mix asphalt pavement aspects of the project and not to any surface preparation requirements dealing with aggregate base courses, milling, or tack and prime coats. Cover surface preparation requirements by adding pertinent sections to the project documents.

This specification utilizes a Quality Assurance and Quality Control (QA/QC) construction management philosophy. Quality Assurance refers to the actions performed by the Government or designated representative to assure the final product meets the job requirements. This specification has been developed for QC testing to be used as a basis of pay. It is recommended that the Government's QA testing include a minimum of 5 percent of the QC tests performed by the Contractor. Results of QC testing are the basis for pay unless there are discrepancies between QC and QA testing. Quality Control also refers to the actions of the Contractor to monitor the construction and production processes and to correct these processes when out of control. Results of QC testing are reported daily on the process control charts maintained by the Contractor. Quality Control is covered in paragraph CONTRACTOR QUALITY CONTROL STAFF and paragraph CONTRACTOR QUALITY CONTROL.

1.1 FULL PAYMENT

1.1.1 Method of Measurement

NOTE: For unit-price contracts, include first bracketed statements and delete the second set. For lump sum contracts, delete the first bracketed statements and include the second set.

Do not delete PART 1 for lump sum Contracts.

[The amount paid for will be the number of metric tons of hot-mix asphalt pavement mixture used in the accepted work. Weigh the hot-mix asphalt pavement mixture after mixing. No separate payment will be made for weight of asphalt binder material incorporated herein.] [Utilize the quantity of hot-mix asphalt pavement, per metric ton placed and accepted, for the purposes of assessing the pay factors stipulated below.]

1.1.2 Basis of Payment

NOTE: For unit-price contracts, include first bracketed statements and delete the second set. For lump sum contracts, delete the first bracketed statements and include the second set. Include prescriptive unit price based on the Government estimate for payment adjustment. Lump sum contracts

should not be used when the job exceeds 1000 metric
tons.

[Quantities of hot-mix asphalt pavement, determined as specified above, will be paid for at respective contract unit prices or at reduced prices adjusted in accordance with paragraphs PERCENT PAYMENT and ACCEPTANCE. Payment will constitute full compensation for furnishing all materials, equipment, plant, and tools; and for all labor and other incidentals necessary to complete work required by this section of the specification.] [The measured quantity of hot-mix asphalt pavement will be paid for and included in the lump sum contract price. If less than 100 percent payment is due based on the pay factors stipulated in paragraph PERCENT PAYMENT and ACCEPTANCE, a unit price per metric ton will be used for purposes of calculating the payment reduction.]

1.2 PERCENT PAYMENT

**NOTE: The basis of percent payment includes
material tests to determine laboratory air voids,
in-place density, smoothness and plan grade which
are needed to determine percent payment.**

When a pavement lot of material fails to meet the specification requirements for 100 percent pay as outlined in the following paragraphs, remove and replace the lot, or accept at a reduced price which will be computed by multiplying the unit price per ton by the lot's pay factor. The lot pay factor is determined by taking the lowest computed pay factor based on either laboratory air voids, in-place density, grade or smoothness (each discussed below). At the end of the project, an average of all lot pay factors will be calculated. If this average lot pay factor exceeds 95.0 percent and no individual lot has a pay factor less than 75.0 percent, then the percent payment for the entire project will be 100 percent of the unit bid price. If the average lot pay factor is less than 95.0 percent, then each lot will be paid for at the unit price multiplied by the lot's pay factor. For any lots which are less than 2000 metric tons, a weighted lot pay factor will be used to calculate the average lot pay factor. When work on a lot is required to be terminated before all sublots are completed, the results from the completed sublots will be analyzed to determine the percent payment for the lot following the same procedures and requirements for full lots but with fewer test results.

1.2.1 Mat and Joint Densities

The average in-place mat and joint densities are expressed as a percentage of the average theoretical maximum density (TMD) for the lot. The average TMD for each lot will be determined as the average TMD of the four random samples per lot. The average in-place mat density and joint density for a lot are determined and compared with Table 1 to calculate a single pay factor per lot based on in-place density, as described below. All density results for a lot will be completed and reported within 24 hours after the construction of that lot. Use the following process to determine the single pay factor for in-place density:

- a. Step 1: Determine the pay factors for mat density and joint density using Table 1.

- b. Step 2: Determine ratio of joint area to mat area. The area associated with the joint is considered to be 3 m wide times the length of completed longitudinal construction joint in the lot. This joint area will not exceed the total lot size. The length of joint to be considered will be that length where a new lane has been placed against an adjacent lane of asphalt pavement, either any cold joint against another lot or any other existing asphalt paved previously. The area associated with the joint is expressed as a percentage of the total lot.
- c. Step 3: Compute the weighted pay factor for the joint using the formula in the example shown in paragraph PAY FACTOR BASED ON IN-PLACE DENSITY.
- d. Step 4: Where freshly placed asphalt pavement abuts old (not in contract) asphalt pavement, determine density at the tie-in longitudinal joint by taking one core per subplot at a random location for each lot of material placed adjacent to the joint. If Step 4 is not applicable, move to Step 5. The size of joint area is 3 m wide by the length of the joint being paved. Locate the center of each of the four cores 150 mm from the edge of the existing pavement. Take each core at a random location along the length of the joint. The requirements for joint density for this lot, adjacent to the existing asphalt joint, are the same as that for the mat density specified in Table 1. For the interface of new asphalt pavement abutting existing asphalt (not in contract) joints at taxiways abutting runways, aprons, or other taxiways, take two additional randomly located cores along each taxiway intersection.
- e. Step 5: Compare weighted pay factor for joint density to pay factor for mat density and select the lowest. This selected pay factor is the pay factor based on density for the lot. When the TMD on both sides of a longitudinal joint is different, the average of these two TMD values will be used as the TMD needed to calculate the percent joint density.

When 0 percent payment is determined for mat density, remove and replace the rejected lot at least 100 mm into the cold lane adjacent to the longitudinal joint. Evaluate this as a new lot per paragraph MAT AND JOINT DENSITIES.

When 0 percent payment is determined for joint density, remove and replace the rejected longitudinal joint with a 3 m wide paving lane that is centered over the joint. This 3 m wide placement will be evaluated as a new lot. When removing and replacing a joint that fails to meet the project requirements, the result will be two additional longitudinal joints. Determine a pay factor for these longitudinal joints by randomly selecting two cores per lot centered on the joint each side of the lot. This will result in four total cores for joint density evaluation. Take the average of the joint density of the four cores to develop a pay factor for joint density determination. Average the new lot TMD values with the adjacent lot TMD values to determine a final average for joint density evaluation. In this case do not use a weighted pay factor. Evaluate the mat density for this lot per paragraph MAT AND JOINT DENSITIES.

Table 1		
Pay Factor Based on In-place Density		
Average Mat Density (4 cores) (Percent of TMD)	Pay Factor, percent	Average Joint Density (4 cores) (Percent of TMD)
94.0 - 96.0	100.0	Above 92.5
93.9	100.0	92.4
93.8 or 96.1	99.9	92.3
93.7	99.8	92.2
93.6 or 96.2	99.6	92.1
93.5	99.4	92.0
93.4 or 96.3	99.1	91.9
93.3	98.7	91.8
93.2 or 96.4	98.3	91.7
93.1	97.8	91.6
93.0 or 96.5	97.3	91.5
92.9	96.3	91.4
92.8 or 96.6	94.1	91.3
92.7	92.2	91.2
92.6 or 96.7	90.3	91.1
92.5	87.9	91.0
92.4 or 96.8	85.7	90.9
92.3	83.3	90.8
92.2 or 96.9	80.6	90.7
92.1	78.0	90.6
92.0 or 97.0	75.0	90.5
below 92.0, above 97.0	0.0 (reject)	below 90.5

1.2.2 Pay Factor Based on In-place Density

An example of the computation of a pay factor (in I-P units only) based on in-place density, is as follows: Assume the following test results for field density made on the lot: (1) Average mat density = 93.2 percent (of lab TMD). (2) Average joint density = 91.5 percent (of lab TMD). (3) Total area of lot = 30,000 square feet. (4) Length of completed longitudinal construction joint = 2,000 feet.

- a. Step 1: Determine pay factor based on mat density and on joint density, using Table 1:

Mat density of 93.2 percent = 98.3 pay factor.

Joint density of 91.5 percent = 97.3 pay factor.

- b. Step 2: Determine ratio of joint area (length of longitudinal joint x 10 feet) to mat area (total paved area in the lot): Multiply the length of completed longitudinal construction joint by the specified 10 feet width and divide by the mat area (total paved area in the lot).

$(2,000 \text{ feet} \times 10 \text{ feet}) / 30000 \text{ square feet} = 0.6667$ ratio of joint area to mat area (ratio).

- c. Step 3: Weighted pay factor (wpf) for joint is determined as indicated below:

$\text{wpf} = \text{joint pay factor} + (100 - \text{joint pay factor}) (1 - \text{ratio})$
 $\text{wpf} = 97.3 + (100 - 97.3) (1 - 0.6667) = 98.2 \text{ percent}$

- d. Step 4: Compare weighted pay factor for joint density to pay factor for mat density and select the smaller:

Pay factor for mat density: 98.3 percent. Weighted pay factor for joint density: 98.2 percent

Select the smaller of the two values as pay factor based on density:
98.2 percent

1.2.3 Payment Adjustment for Smoothness (Final Wearing Surface Only)

NOTE: When Profilograph testing is not required, delete the following paragraph for pay adjustment for smoothness. This paragraph may be deleted for projects where a profilograph cannot record 161 meters in length. Profilograph testing is required for runways, taxiways and landing zone pavements.

1.2.3.1 Longitudinal Smoothness

Evaluate smoothness per paragraph PROFILOGRAPH TESTING. Determine the pay factor for longitudinal smoothness by entering Table 2.

Table 2	
Pay Factor for Smoothness	
Profile Index of a 0.1 km segment of a lot exceeds the tolerance specified in paragraph SURFACE SMOOTHNESS by:	Pay Factor, Percent
0.0 mm per km	100.0

Table 2	
Pay Factor for Smoothness	
Profile Index of a 0.1 km segment of a lot exceeds the tolerance specified in paragraph SURFACE SMOOTHNESS by:	Pay Factor, Percent
greater than 0.0 mm per km but less than 16.0 mm per km	95.0
16.0 mm per km but less than 32.0 mm per km 2.0 inches per mile	90.0
32.0 mm per km but less than 47.0mm per km	75.0
47.0 mm per km or greater	Remove and Replace

1.2.4 Laboratory Air Voids and Theoretical Maximum Density

Laboratory air voids will be calculated in accordance with ASTM D3203/D3203M or KS F 2364 by determining the density of each lab compacted specimen using the laboratory-prepared, thoroughly dry method in ASTM D2726/D2726M or KS F 2353 and determining the theoretical maximum density (TMD) of four of the sublots using ASTM D2041/D2041M or KS F 2366. Laboratory air void calculations for each lot will use the average TMD values obtained for the lot. The mean absolute deviation of the four laboratory air void contents (one from each subplot) from the JMF air void content will be evaluated and a pay factor determined from Table 3. All laboratory air void tests will be completed and reported within 24 hours after completion of construction of each lot. The TMD is also used for computation of in-place density, as required in paragraph MAT AND JOINT DENSITIES above.

1.2.4.1 Mean Absolute Deviation

An example of the computation of mean absolute deviation for laboratory air voids is as follows: Assume that the laboratory air voids are determined from 4 random samples of a lot (where 3 specimens were compacted from each sample). The average laboratory air voids for each subplot sample are determined to be 3.5, 3.0, 4.0, and 3.7. Assume that the target air voids from the JMF is 4.0. The mean absolute deviation is then:

$$\text{Mean Absolute Deviation} = (|3.5 - 4.0| + |3.0 - 4.0| + |4.0 - 4.0| + |3.7 - 4.0|)/4$$

$$= (0.5 + 1.0 + 0.0 + 0.3)/4 = (1.8)/4 = 0.45$$

The mean absolute deviation for laboratory air voids is determined to be 0.45. It can be seen from Table 3 that the lot's pay factor based on laboratory air voids, is 100 percent.

Table 3	
Pay Factor Based on Laboratory Air Voids	
Mean Absolute Deviation of Lab Air Voids from JMF	Pay Factor, Percent
0.60 or less	100
0.61 - 0.80	98
0.81 - 1.00	95
1.01 - 1.20	90
Above 1.20	reject (0)

1.2.5 Pay Factor Based on Plan Grade

NOTE: The plan grade requirements specified below are for the final wearing surface only. If there is a requirement to test and control the grade and smoothness for the intermediate courses, for example, when the intermediate courses will be exposed to traffic, slight modifications to this specification will be required. Designer is responsible for providing spot elevations at 15 m or less and cross section in a frequency that is satisfactory for the project. Spot elevations should be provided on a grid or mesh pattern. These spot elevations will be utilized to ensure the construction adheres to the design and to determine percent payment during production.

Evaluate plan grade per paragraph PLAN GRADE. Use Table 4 for determining Pay Factor for Plan Grade. Evaluate plan grade on a lot basis.

Table 4	
Pay Factor for Plan Grade	
Percent of All Measurements Outside Tolerance	Pay Factor, percent
Less than 5	100
Greater than or equal to 5 but less than 10	90
Greater than or equal to 10 but less than 15	75
Greater than or equal to 15	Remove and replace the surface lift

1.3 REFERENCES

NOTE: This paragraph is used to list the publications cited in the text of the guide specification. The publications are referred to in

the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a Reference Identifier (RID) outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text will automatically be deleted from this section of the project specification when you choose to reconcile references in the publish print process.

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

AMERICAN ASSOCIATION OF STATE HIGHWAY AND TRANSPORTATION OFFICIALS
(AASHTO)

AASHTO M 156 (2013; R 2017) Standard Specification for Requirements for Mixing Plants for Hot-Mixed, Hot-Laid Bituminous Paving Mixtures

AASHTO T 329 (2015) Standard Test Method for Moisture Content of Hot Mix Asphalt (HMA) by Oven Method

ASPHALT INSTITUTE (AI)

AI MS-2 (2015) Asphalt Mix Design Methods

ASTM INTERNATIONAL (ASTM)

ASTM C29/C29M (2023) Standard Test Method for Bulk Density ("Unit Weight") and Voids in Aggregate

ASTM C88 (2018) Standard Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate

ASTM C117 (2023) Standard Test Method for Materials Finer than 75-um (No. 200) Sieve in Mineral Aggregates by Washing

ASTM C127 (2024) Standard Test Method for Density, Relative Density (Specific Gravity), and Absorption of Coarse Aggregate

ASTM C128 (2022) Standard Test Method for Density, Relative Density (Specific Gravity), and Absorption of Fine Aggregate

ASTM C131/C131M	(2020) Standard Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine
ASTM C136/C136M	(2019) Standard Test Method for Sieve Analysis of Fine and Coarse Aggregates
ASTM C142/C142M	(2017; R 2023) Standard Test Method for Clay Lumps and Friable Particles in Aggregates
ASTM C566	(2013) Standard Test Method for Total Evaporable Moisture Content of Aggregate by Drying
ASTM C1252	(2017) Standard Test Methods for Uncompacted Void Content of Fine Aggregate (as Influenced by Particle Shape, Surface Texture, and Grading)
ASTM D75/D75M	(2019) Standard Practice for Sampling Aggregates
ASTM D140/D140M	(2016) Standard Practice for Sampling Asphalt Materials
ASTM D242/D242M	(2009; R 2014) Mineral Filler for Bituminous Paving Mixtures
ASTM D979/D979M	(2015) Sampling Bituminous Paving Mixtures
ASTM D2041/D2041M	(2011) Theoretical Maximum Specific Gravity and Density of Bituminous Paving Mixtures
ASTM D2172/D2172M	(2017; E 2018) Standard Test Methods for Quantitative Extraction of Asphalt Binder from Asphalt Mixtures
ASTM D2419	(2014) Sand Equivalent Value of Soils and Fine Aggregate
ASTM D2489/D2489M	(2016) Standard Test Method for Estimating Degree of Particle Coating of Asphalt Mixtures
ASTM D2726/D2726M	(2019) Standard Test Method for Bulk Specific Gravity and Density of Non-Absorptive Compacted Bituminous Mixtures
ASTM D3203/D3203M	(2017) Standard Test Method for Percent Air Voids in Compacted Asphalt Mixtures
ASTM D3665	(2012; R 2017) Standard Practice for Random Sampling of Construction Materials
ASTM D3666	(2016) Standard Specification for Minimum

Requirements for Agencies Testing and
Inspecting Road and Paving Materials

ASTM D4125/D4125M	(2010) Asphalt Content of Bituminous Mixtures by the Nuclear Method
ASTM D4791	(2019) Flat Particles, Elongated Particles, or Flat and Elongated Particles in Coarse Aggregate
ASTM D4867/D4867M	(2009; R 2014) Effect of Moisture on Asphalt Concrete Paving Mixtures
ASTM D5361/D5361M	(2016) Standard Practice for Sampling Compacted Asphalt Mixtures for Laboratory Testing
ASTM D5444	(2015) Mechanical Size Analysis of Extracted Aggregate
ASTM D5821	(2013; R 2017) Standard Test Method for Determining the Percentage of Fractured Particles in Coarse Aggregate
ASTM D6307	(2019) Standard Test Method for Asphalt Content of Asphalt Mixture by Ignition Method
ASTM D6373	(2023) Standard Specification for Performance Graded Asphalt Binder
ASTM D6926	(2020) Standard Practice for Preparation of Asphalt Mixture Specimens Using Marshall Apparatus
ASTM D6927	(2015) Standard Test Method for Marshall Stability and Flow of Bituminous Mixtures
ASTM E1274	(2018; R 2024) Standard Test Method for Measuring Pavement Roughness Using a Profilograph

KOREAN INDUSTRIAL STANDARDS (KS)

KS F 2309	(2024) Standard Test Method for Determining the Amount of Material Finer than No.200 Sieve of Soils by Washing
KS F 2340	(2024) Standard test method for sand equivalent value of granular soils and fine aggregates
KS F 2352	(2020) Standard test method for effect of water on cohesion of compacted asphalt mixtures
KS F 2353	(2010; R 2022) Standard test method for specific bulk gravity of compacted asphalt mixtures

KS F 2354	(2013; R 2023) Standard test method for asphalt content from asphalt paving mixtures
KS F 2360	(2016; R 2021) Standard test method for degree of particle coating of asphalt-aggregate mixture
KS F 2364	(2024) Standard test method for percent air voids in compacted dense and open asphalt mixtures
KS F 2366	(2010; R 2022) Standard test method for theoretical maximum specific gravity of asphalt mixtures
KS F 2372	(2020) Standard test method for moisture or volatile distillates in asphalt paving mixtures
KS F 2384	(2013; R 2023) Test method for uncompacted void content of fine aggregate
KS F 2389	(2024) Performance grade for asphalt binder
KS F 2501	(2017; R 2022) Standard Test Method for Sampling Aggregates
KS F 2502	(2019; R 2024) Standard Test Method for Sieve Analysis of Aggregates
KS F 2503	(2019; R 2024) Standard test method for density and water absorption of coarse aggregates
KS F 2504	(2020; R 2024) Standard test method for density and water absorption rate of fine aggregates
KS F 2505	(2017; R 2022) Standard test method for bulk density and solid contents in aggregates
KS F 2507	(2024) Test method for soundness of aggregates by use of sodium sulfate
KS F 2508	(2007; R 2022) Standard test method for resistance to abrasion of coarse aggregate by use of the Los Angeles machine
KS F 2575	(2013; R 2023) Test method for flat or elongated particles in coarse aggregate
KS F 3501	(2022) Filler for hot mix asphalt pavement

[1.4 AIRFIELD ASPHALT PAVING WORKSHOP

NOTE: TSMCX provides airfield asphalt paving workshops regardless of project management organization - USACE, AFCEC or NAVFAC.

For USACE managed projects, review ER 1110-34-1 TRANSPORTATION SYSTEMS MANDATORY CENTER OF EXPERTISE and retain the following paragraph if deemed a Mandatory Service or if the project development team requests it as an Elective Service.

For AFCEC and NAVFAC managed projects, the below airfield asphalt paving workshop is optional. Appropriate coordination with TSMCX, AFCEC, or NAVFAC is recommended prior to specifying the airfield asphalt paving workshop.

Select MTV Operator if required by paragraph MATERIAL TRANSFER VEHICLE.

Attend a one day paving workshop held in advance of asphalt paving. Acquire a facility for the workshop in the vicinity of the installation, or other appropriate location, as approved by the Government. Provide a facility that includes at a minimum, parking and seating for forty attendees, audio/visual with standard connections, including TV, projector, screen and any other items as required for display of digital presentations, and access to Wi-Fi. Coordinate schedule with the Government. Attendance requirements apply to each paving crew anticipated to be on the project. At a minimum, the following attendees are required.

- a. Project Superintendent
- b. Paving Superintendent or Foreman(s)
- c. Paving Machine Operator(s)
- d. Asphalt Plant Operator(s)
- e. Airfield Asphalt Pavement Quality Control Manager
- f. Airfield Asphalt Pavement Inspector
- g. Airfield Asphalt Pavement Laboratory Technicians
- h. Roller Operators
- i. Aggregate Supplier(s)
- j. MTV Operator(s)

1.5 SUBMITTALS

NOTE: Review submittal description (SD) definitions in Section 01 33 00 SUBMITTAL PROCEDURES and edit the following list, and corresponding submittal items in the text, to reflect only the submittals required for the project. The Guide Specification technical editors have classified those items that

require Government approval, due to their complexity or criticality, with a "G." Generally, other submittal items can be reviewed by the Contractor's Quality Control System. Only add a "G" to an item, if the submittal is sufficiently important or complex in context of the project.

For Army projects, fill in the empty brackets following the "G" classification, with a code of up to three characters to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy and Air Force projects.

The "S" classification indicates submittals required as proof of compliance for sustainability Guiding Principles Validation or Third Party Certification and as described in Section 01 33 00 SUBMITTAL PROCEDURES.

Choose the first bracketed item for Navy and Air Force projects, or choose the second bracketed item for Army projects.

Government approval is required for submittals with a "G" or "S" classification. Submittals not having a "G" or "S" classification are for information only. When used, a code following the "G" classification identifies the office that will review the submittal for the Government. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

SD-01 Preconstruction Submittals

Equipment; G

SD-02 Shop Drawings

Placement Plan; G

SD-03 Product Data

Diamond Grinding Plan; G

Mix Design; G

Contractor Quality Control; G

SD-04 Samples

Aggregates

Asphalt Binder

SD-06 Test Reports

Aggregates; G

QC Monitoring

Pavement Lots; G

Notification

SD-07 Certificates

Asphalt Binder; G

Testing Laboratory

Airfield Asphalt Pavement QC Manager

Airfield Asphalt Pavement Inspector

Airfield Asphalt Pavement Laboratory Technician

1.6 CONTRACTOR QUALITY CONTROL STAFF

NOTE: Select UFGS 01 45 00 for Army, Air Force, and Navy projects. Select appropriate second set of bracketed text if asphalt pavement is associated with other more predominant features of work (e.g. hangar projects, concrete runways with asphalt shoulders, etc.).

The airfield asphalt certification program is intended to increase quality of construction for work performed under this specification. The certification program will provide knowledge to the project team members as it relates to airfield asphalt. Intended audience is the Contractor and Government personnel. The below paragraph should be modified or the general provisions of the contract should be modified to require Title II inspectors or third party laboratory firms attend the certification program.

Reference Section 01 45 00 QUALITY CONTROL for Contractor personnel qualification requirements along with the information included below. The Airfield Asphalt Pavement QC Manager is a separate person and is in addition to the CQC System Manager identified in Section 01 45 00 QUALITY CONTROL. The Airfield Asphalt Pavement QC Manager will report to and assist the project CQC System Manager. Submit certifications for Contractor Quality Control Staff in the following areas:

- a. Airfield Asphalt Pavement QC Manager⁽¹⁾: The QC manager will oversee all QC testing and inspection, review asphalt pavement transmittals prior to submission to the Government, be responsible for making mix design adjustments, and in charge of all other activities related to performance. The QC manager will also ensure that daily reports and necessary transmittals arrive for Government review as specified.

- b. **Airfield Asphalt Pavement Inspector**⁽¹⁾: The Inspector will be available on the project during all paving operations. The Inspector is responsible for identifying observed paving issues and ensuring these issues are addressed by the Contractor Quality Control staff.
- c. **Airfield Asphalt Pavement Laboratory Technician**⁽¹⁾: The Technician will be responsible for conducting laboratory tests. The Airfield Asphalt Pavement Technician will be present in the laboratory anytime laboratory testing is underway.

⁽¹⁾: Registration for the Airfield Asphalt Pavement Certification Program can be found at www.airfieldasphaltpcert.com.

If the Quality Control personnel is not certified listed above, the personnel's expertise to perform QC of asphalt must be verified by the Contracting Officer. The personnel must be certified from Human Resources Development Service of Korea or Korean Standard Association as construction materials testing or QC manager.

1.7 ACCEPTANCE

NOTE: It is recommended that an independent material testing firm be hired by the Contractor to provide the acceptance testing for the project. It is also recommended to keep the Government QA testing separate and distinct from the Contractor's QC testing for all airfield projects.

The acceptance testing program includes material tests to determine laboratory air voids and in-place density, which are needed to determine percent payment. The Contractors acceptance testing laboratory will also conduct tests to monitor aggregate gradation, asphalt content, and volumetric properties.

For projects with less than 2000 total **metric tons** the entire project can be considered as a single lot. In this case, subplot sampling could occur over several days' production, which could lead to higher subplot variability.

1.7.1 Acceptability of Work

Acquire the services of an independent commercial laboratory to perform acceptance testing. Acceptance of the plant produced mix and in-place requirements will be on a lot to lot basis. The materials and the pavement itself will be accepted on the basis of production testing. The Government may make check tests from split samples to validate the results of the production testing. Testing performed by the Government does not reduce the required testing of the independent commercial laboratory. Split samples will be taken for Government testing to reduce the variability between the independent commercial laboratory and the Government's test results. When the difference between the independent commercial laboratory and the Government's test results for split samples

exceed the acceptable range of two results for multi-laboratory precision for the appropriate test method (i.e. ASTM) then at least one of the laboratories is determined to be in error. An evaluation of procedures and equipment in both laboratories will be made to determine the cause(s) for the differences. Develop steps to correct procedures and equipment to bring multi-laboratory precision to within acceptable limits.

1.7.2 Acceptance Requirements

Provide all sampling and testing required for acceptance and payment adjustment. Where appropriate, adjustments in payment for individual lots of asphalt pavement will be made based on laboratory air voids, in-place density, smoothness, and grade in accordance with the following paragraphs. Surface smoothness and grade determinations will be made on the lot as a whole. Exceptions or adjustments to this will be made in situations where the mix within one lot is placed as part of both the intermediate and surface courses, thus smoothness and grade measurements for the entire lot cannot be made.

1.7.3 Pavement Lots

A standard lot for all requirements is equal to one day's production or 2,000 metric tons, whichever is smaller. Divide each lot into four equal sublots in order to evaluate laboratory air voids and in-place density. When operational conditions cause a lot to be terminated before the specified four sublots have been completed, use the following procedure to adjust the lot size and number of tests for the lot. Where three sublots have been completed, they constitute a lot. Where one or two sublots have been completed, incorporate them into the next lot and the total number of sublots (i.e. 5 or 6 sublots) is used for acceptance criteria. Maintain 4 sublots when possible. Include partial lots at the end of asphalt production into the previous lot. When more than one plant is simultaneously producing asphalt for the project, apply the lot size separately for each plant. Complete and report all asphalt testing including but not limited to aggregate gradation, asphalt content, theoretical maximum density, laboratory air voids, and in-place density testing within 24 hours, unless otherwise stated, after construction of each lot.

1.7.4 Sublot Sampling

Obtain one random mixture sample from each sublot in accordance with ASTM D979/D979M from a loaded truck or another approved location for determining laboratory air voids, theoretical maximum density, Contractor Quality Control, and for any additional testing as directed the Government. Representative samples will be selected from random trucks, using commonly recognized methods of assuring randomness conforming to ASTM D3665 and employing tables of random numbers or computer programs. Laboratory air voids will be determined from three laboratory compacted specimens of each sublot sample in accordance with ASTM D3203/D3203M or KS F 2364. The specimens will be compacted within 2 hours of the time the mixture was loaded into trucks at the asphalt plant. Samples will not be reheated prior to compaction and insulated containers will be used as necessary to maintain the temperature.

1.7.5 Additional Sampling and Testing

The Government reserves the right to direct additional samples and tests for any area which appears to deviate from the specification

requirements. The cost of any additional testing will be paid for by the Contractor. Testing in these areas will be treated as a separate lot. Payment will be made for the quantity of asphalt pavement represented by these tests in accordance with the provisions of this section.

1.7.6 Theoretical Maximum Density (TMD)

Measure theoretical maximum density one time for each subplot in accordance with [ASTM D2041/D2041M](#) or [KS F 2366](#) for purposes of calculating laboratory air voids and determining in-place density. The average TMD for each lot will be determined as the average TMD of the random subplot samples. When the TMD on both sides of a longitudinal joint is different, the average of these two TMD values will be used as the TMD needed to calculate the percent joint density.

1.7.7 Laboratory Air Voids

**NOTE: Select the appropriate tailoring option for
the Marshall or Superpave Methods.**

Prepare one set of laboratory compacted specimens for each subplot in accordance with [ASTM D6926](#) using the hand-held hammer for the Marshall Method. Provide three test specimens prepared from the same sample for each set of laboratory compacted specimens. Compact the specimens within 2 hours of the time the mixture was loaded into trucks at the asphalt plant. Do not reheat samples prior to compaction. Provide insulated containers as necessary to maintain the sample temperature. Measure the bulk density of laboratory compacted specimens in accordance with [ASTM D2726/D2726M](#) or [KS F 2353](#). Determine laboratory air voids from one set (three laboratory compacted specimens) for each subplot sample in accordance with [ASTM D3203/D3203M](#) or [KS F 2364](#).

1.7.8 In-place Density

Obtain one random [150 mm](#) diameter core from the mat and joint of each subplot in accordance with [ASTM D5361/D5361M](#) for determining in-place density. Where different job mix formulas are required as part of the same project, and are adjacent to one another, follow the same joint density sampling and joint density testing instructions of this specification. Cut samples neatly with a diamond core drill bit. Obtain random cores that are the full thickness of the layer being placed. Select core locations randomly using the procedures contained in [ASTM D3665](#). Locate cores for mat density no closer than [300 mm](#) from a transverse or longitudinal joint. Center all cores for joint density on the joint. Discard samples that are clearly defective as a result of sampling and take an additional random core. When the random core is less than [25 mm](#) thick, it will not be included in the analysis. In this case, obtain another random core sample. Clean and tack coat dry core holes before filling with asphalt mixture. Fill all core holes with asphalt mixture and compact using a manual (hand-held) Marshall hammer to the density specified. Provide all tools, labor, and materials for cutting samples, cleaning, and filling the cored pavement. Measure in-place density in accordance with [ASTM D2726/D2726M](#) or [KS F 2353](#) using each core obtained from the mat and joint.

1.7.9 Surface Smoothness

After the final rolling, but not later than 24 hours after placement, test the surface of the pavement in each entire lot by use of a straightedge and/or profilograph to reveal surface irregularities exceeding the tolerances specified. Straightedge is used for all lifts. Use the profilograph method for testing longitudinal smoothness on surface lifts only, except for paving lanes less than 161 m, and at the ends of the paving limits for the project. Use straightedge method for all other measurements. If any pavement areas are diamond ground, retest these areas immediately after diamond grinding and submit results to the Government for evaluation. At a minimum, provide enough information to determine exact location of grinding (station and offset from centerline), smoothness results, and the associated lot(s) pay factor for smoothness. Follow requirements of paragraph DIAMOND GRINDING if diamond grinding is required to correct smoothness. Where drawings show required deviations from a plane surface (for instance crowns, drainage inlets), finish the surface to meet the approval of the Government.

1.7.9.1 Straightedge Testing

**NOTE: Select bracketed text when paving lots are
anticipated to be less than 1/10 mile longitudinally.**

Provide finished surfaces of the pavements within the tolerances specified in Table 5 when checked with an approved 4 m straightedge. Start longitudinal and transverse straightedge testing with one-half the length of the straightedge at the edge of pavement section being tested and then moved ahead one-half the length of the straightedge for each successive measurements. Perform continuous tests across all joints. Determine the amount of surface irregularity by placing the freestanding (unleveled) straightedge on the pavement surface and allowing it to rest upon the two highest spots covered by its length, and measuring the maximum gap between the straightedge and the pavement surface in the area between these two high points. Use the straightedge to also measure abrupt changes in surface smoothness. Abrupt changes in the surface can be visually observed where the surface exhibits irregularities or discontinuities. Surface areas with obvious smoothness defects will be tested with the straightedge to determine the limits of the surface not meeting the tolerance requirements in Table 5. Do not perform straightedge measurements across grade changes or cross slope transitions.

Perform transverse measurements perpendicular to centerline every 15 m or more often as determined by the Government. [For longitudinal measurements, test parallel to the centerline of paving; at the center of paving lanes when widths of paving lanes are less than 6 m; and at the third points of paving lanes when widths of paving lanes are 6 m or greater.] After two full lots have been placed with an average of less than five percent of measurements out, a request can be made to reduce the testing frequency at a rate approved by the Government. Report all individual straightedge measurements coinciding with project stationing in each paving lot report.

Table 5		
Straightedge Surface Smoothness		
Pavement Category	Direction of Testing	Tolerance, mm
Runways, taxiways, and landing zones	Longitudinal	3
	Transverse	6
Shoulders (outside edge stripe)	Longitudinal	6
	Transverse	6
Calibration hardstands and compass swinging bases	Longitudinal	3
	Transverse	3
All other airfield pavements (including overruns) and helicopter paved areas	Longitudinal	6
	Transverse	6

1.7.9.2 Profilograph Testing

Test the entire lot in the longitudinal direction with an approved California-type profilograph per ASTM E1274. Provide equipment that utilizes electronic recording and automatic computerized reduction of data to indicate "must-grind" bumps and the Profile Index for the pavement. Use a "blanking band" that is 5 mm wide and the "bump template" spanning 25 mm with an offset of 10 mm. Perform the longitudinal testing at the centerline of each paving lot. If paving widths are greater than 5 m test at the centerline and at 1/8th points from each side of the lot. Record the location and data from all profilograph measurements. Compute the profile index for each pass of the profilograph in each 0.1 km segment. Provide a profile index not greater than 110 mm per km per segment for runways, taxiways and landing zones. Provide a profile index not greater than 140 mm per km per segment for all other pavements. Reduce any bumps ("must grind" areas) shown on the profilograph trace which exceed 10 mm in height by diamond grinding until they do not exceed 7.5 mm when retested. Taper diamond grinding in all directions to provide smooth transitions to areas not requiring diamond grinding. Skin patching for correcting low areas and planing or milling for correcting high areas are not permitted. When the profile index of a lot exceeds the tolerance specified, determine pay factor using Table 2. Diamond grinding is allowed to reduce the scallop height of pavement to decrease the lot profile index as long as minimum lift thickness per Contract is met and the diamond grinding limit per paragraph SURFACE SMOOTHNESS is not exceeded. Perform additional profilograph testing in all areas corrected by diamond grinding. Provide profilograph operated by an approved, factory-trained operator. Provide a digital copy of all test results to the Government in each paving lot report.

[1.7.9.3 Final Profilograph Testing

NOTE: Select this paragraph if project includes long linear pavements such as a runway or taxiway where evaluation of between lot transitions are desired. Appropriate projects would include new

**construction, complete mill/overlay or
reconstruction of a runway/taxiway or other similar
airfield feature. Edit bracketed text for the
airfield feature(s) to be evaluated.**

After all paving on the [runway][taxiway] is complete, perform final profilograph testing in the longitudinal direction per paragraph PROFILOGRAPH TESTING with the following changes. Operate the profilograph the full length of the asphalt pavement on the [runway][taxiway] to facilitate testing of the smoothness between lots and to evaluate the transition of any transverse joints. Provide pavements having an average total profile index less than 158 mm per km. Operate the profilograph 0.3 m left and right of centerline and 4.5 m right and left of project centerline (four total traces). Correct any "must grind" areas by diamond grinding or by removing and replacing full depth of the surface course. Reevaluate the pavement with a second profilograph run after corrections to ensure an average profile index of 158 mm per km or less is achieved. Final profilograph testing is to be done in addition to the profilograph traces being performed on a lot basis. Provide a digital copy of the test results to the Government prior to full acceptance of the pavement.]

1.7.10 Plan Grade

Within 5 working days after completion of a particular lot incorporating the final wearing course, test the lot for conformance with specified plan grade requirements. Provide a final wearing surface of pavement conforming to the elevations and cross sections and not vary more than 9 mm for runways and landing zones or 15 mm for taxiways, aprons and shoulders. Deviation from the plan elevations will not be permitted in areas of pavements where closer conformance with planned elevation is required for the proper functioning of drainage and other appurtenant structures involved. The grade will be determined by running lines of levels at intervals of 15 m, or less, longitudinally that coincides with the project spot elevations and lateral spacing to match the paving lane width (after cut back). In areas where the grade exceeds the tolerance by more than 50 percent, remove the surface lift full depth and replace the lift with asphalt pavement to meet specification requirements, at no additional cost to the Government. Match finished surfaces at juncture with other pavements with finished surfaces of abutting pavements except for where paragraph ASPHALT PAVEMENT-PORTLAND CEMENT CONCRETE JOINTS apply. Diamond grinding can be used to remove high spots to meet grade requirements. Skin patching for correcting low areas or planing or milling for correcting high areas is not permitted. Provide finished surface grades in record drawing format showing design and constructed elevations which are stamped and signed by a licensed surveyor. Provide a comparison of the as-built grades to the design grades and determine a percentage of individual measurements exceeding the tolerances specified and determine pay factor per paragraph PAY FACTOR BASED ON PLAN GRADE. Submit the survey CAD files to the Government for record purposes. Submit all files including the calculation for percent measurements in each paving lot report.

1.8 Laboratory Accreditation and Validation

**NOTE: For Army managed projects, keep the bracketed
text. For Air Force, and Navy, managed projects,
utilization of the USACE Materials Testing Center**

(MTC) Validated Laboratory is optional.

Provide laboratories used to develop the Job Mix Formula (JMF), perform acceptance testing, and Contractor Quality Control testing that meet the requirements of **ASTM D3666**. Perform all required test methods by an accredited and validated laboratory including field standards. Schedule and provide payment for laboratory inspections. Additional payment or a time extension due to failure to acquire the required laboratory accreditation is not allowed. The Government will inspect the laboratory equipment and test procedures prior to the start of asphalt pavement operations for conformance with **ASTM D3666**. In addition, all testing laboratories performing JMF, acceptance testing and Contractor Quality Control requires USACE validation by the Material Testing Center (MTC) for both parent laboratory and plant testing laboratory. Validation on all laboratories is required to remain current throughout the duration of the paving project. Contact the MTC, Geotechnical and Environmental Engineering Branch, Far East District, manager for costs and scheduling. Submit a certificate of compliance signed by the manager of the laboratory stating that it meets these requirements to the Government prior to the start of construction. At a minimum, include the following certifications:

- a. Qualification(s) and certification(s) of personnel; laboratory manager, supervising technician, and testing technicians.
- b. A listing of equipment, with calibration dates, to be used in developing the job mix.
- c. A copy of the laboratory's quality control system.

1.9 ENVIRONMENTAL REQUIREMENTS

NOTE: The temperature requirements in Table 6 are included to avoid problems with the Contractor achieving density because the mix cools too fast. Waivers to these requirements, for isolated incidences during production, are applicable if the density requirements are still met.

Do not place asphalt pavement upon a wet surface or when the surface temperature of the underlying course is less than specified in Table 6. The temperature requirements may be waived by the Government, if requested; provided all other requirements, including in-place density, are met.

Table 6	
Surface Temperature Limitations of Underlying Course	
Mat Thickness, mm	Degrees C
75 or greater	4
Less than 75	7

PART 2 PRODUCTS

2.1 SYSTEM DESCRIPTION

This section is intended to stand alone for construction of asphalt pavement. However, where the construction covered herein interfaces with other sections, construct each interface to conform to the requirements of both this section and the other section, including tolerance for both.

Perform the work consisting of pavement courses composed of mineral aggregate and asphalt material heated and mixed in a central mixing plant and placed on a prepared course. Provide [hot-mix asphalt \(HMA\)](#) pavement designed and constructed in accordance with this section conforming to the lines, grades, thicknesses, and typical cross sections shown on the drawings. Construct each course to the depth, section, or elevation required by the drawings and rolled, finished, and approved before the placement of the next course (adjacent to or above). Submit proposed [Placement Plan](#), indicating lane widths, longitudinal joints, and transverse joints for each course or lift.

2.2 [Equipment](#)

Provide product data for all components below.

2.2.1 Asphalt Mixing Plant

Provide plants used for the preparation of asphalt mixture conforming to the requirements of [AASHTO M 156](#), including calibration data.

2.2.1.1 Truck Scales

Weigh the asphalt mixture on approved scales, or on certified public scales at no additional expense to the Government. Inspect and seal scales at least annually by an approved calibration laboratory.

2.2.1.2 Inspection of Plant

Provide access to the Government at all times, to all areas of the plant for checking adequacy of equipment; inspecting operation of the plant; verifying weights, proportions, and material properties; checking the temperatures maintained in the preparation of the mixtures and for taking samples. Provide assistance as requested, for the Government to procure any desired samples. Plant operation and Plant laboratory must be inspected every two years and one year, respectively by Material Testing Laboratory (MTL), Geotechnical and Environmental Engineering Branch, Far East District.

2.2.1.3 Storage Silos

The asphalt mixture may be stored in non-insulated storage silos for a period of time not exceeding 3 hours. The asphalt mixture may be stored in insulated storage silos for a period of time not exceeding 8 hours. No differences in the mix removed from silos and the mix loaded into trucks are allowed.

2.2.2 Hauling Equipment

Provide trucks used for hauling asphalt mixture that have tight, clean, and smooth metal beds. To prevent the mixture from adhering to them,

lightly coat the truck beds with a minimum amount of paraffin oil, lime solution, or other approved material. Do not use petroleum based products as a release agent. Cover the bed of each truck with a tarp or other suitable cover at all times during transport. When necessary to ensure that the mixture is delivered to the site at the specified temperature, provide insulated or heated truck beds with covers (tarps) that are securely fastened.

2.2.3 Material Transfer Vehicle (MTV)

NOTE: A Material Transfer Vehicle (MTV) is required for runway, taxiway, landing zone, overruns and apron construction. The use of an MTV is optional for shoulder construction. MTV is recommended for all pavements where the weight of the MTV will not damage the pavement structure.

Provide a self-propelled MTV with a swing conveyor that delivers material to the paver from outside the paving lane and without making contact with the paver. Provide MTV capable to move back and forth between the hauling equipment and the paver providing material transfer to the paver, while allowing the paver to operate at a constant speed. Provide Material Transfer Vehicle with remixing and a minimum onboard storage capability of 13 metric tons.

2.2.4 Asphalt Pavers

Provide mechanical spreading and finishing equipment consisting of a self-powered paver, capable of spreading and finishing the mixture to the specified line, grade, and cross section. Provide paver with a vibrating screed capable of placing a uniform mixture to meet the specified thickness, smoothness, and grade without physical or temperature segregation, the full width of the material being placed. Provide a screed that effectively produces a finished surface of the required evenness and texture without tearing, shoving, or gouging the mixture. Provide information on the tractor(s) and screed(s) proposed for use.

2.2.4.1 Receiving Hopper

Provide paver with a receiving hopper of sufficient capacity to permit a uniform spreading operation and a distribution system to place the mixture uniformly in front of the screed without segregation.

2.2.4.2 Automatic Grade Controls

NOTE: Delete information on automatic grade control if not needed. Automatic grade control is needed when the design requires elevations for the asphalt pavement surface. Many maintenance and rehabilitation projects require an overlay thickness and do not specify actual grades.

If an automatic grade control device is used, provide a paver equipped with a control system capable of automatically maintaining the specified screed elevation that is automatically actuated from either a reference

line or through a system of mechanical sensors or sensor-directed mechanisms or devices which maintain the paver screed at a predetermined transverse slope and at the proper elevation to obtain the required surface. Provide transverse slope controller capable of maintaining the screed at the desired slope within plus or minus 0.1 percent. Do not use the transverse slope controller to control grade. Provide controls capable of working in conjunction with any of the following attachments:

- a. Ski-type device of not less than 9.14 m in length.
- b. Taut stringline set to grade.
- c. Short ski or shoe for joint matching.
- d. Laser control.
- e. GPS control.

2.2.5 Rollers

Provide rollers in good condition and operated at slow speeds to avoid displacement of the asphalt mixture. Provide sufficient number, type, and weight of rollers to compact the mixture to the required density while it is still in a workable condition. Do not use equipment which causes excessive crushing of the aggregate.

2.2.6 Diamond Grinding

Those performing diamond grinding are required to have a minimum of three years experience in diamond grinding of airfield pavements. In areas not meeting the specified limits for surface smoothness and plan grade, reduce high areas to attain the required smoothness and grade, except as depth is limited below. Reduce high areas by diamond grinding the asphalt pavement with approved equipment after the asphalt pavement is at a minimum age of 14 days. Perform diamond grinding by sawing with saw blades impregnated with an industrial diamond abrasive. Assemble the saw blades in a cutting head mounted on a machine designed specifically for diamond grinding that produces the required texture and smoothness level without damage to the asphalt pavement. Provide diamond grinding equipment with saw blades that are 3 mm wide, a minimum of 60 blades per 300 mm of cutting head width, and capable of cutting a path a minimum of 0.9 m wide. Diamond grinding equipment that causes raveling, fracturing of aggregate, or disturbance to the underlying material will not be allowed. The maximum area corrected by diamond grinding the surface of the asphalt pavement is 10 percent of the total area of any subplot. The maximum depth of diamond grinding is 12 mm. Provide diamond grinding machine equipped to flush and vacuum the pavement surface. Dispose of all debris from diamond grinding operations off Government property. Prior to diamond grinding, submit a [Diamond Grinding Plan](#) for review and approval. At a minimum, include the daily reports for the deficient areas, the location and extent of deficiencies, corrective actions, and equipment. Remove and replace all pavement areas requiring plan grade or surface smoothness corrections in excess of the limits specified.

Prior to production diamond grinding operations, perform a test section at the approved location, consisting of a minimum of two adjacent passes with a minimum length of 12 m to allow evaluation of the finish and transition between adjacent passes. Production diamond grinding operations cannot be performed prior to approval.

2.3 AGGREGATES

For Design-Bid-Build projects, select the first
bracketed text. For Design-Build projects, select
the second bracketed text..

Sample aggregates in the presence of a Government Representative. Obtain samples in accordance with **ASTM D75/D75M** or **KS F 2501** and be representative of the materials to be used for the project. Provide aggregates consisting of crushed stone, crushed gravel, crushed slag, screenings, natural sand and mineral filler, as required. The portion of material retained on the **4.75 mm** (No. 4) sieve is coarse aggregate. The portion of material passing the **4.75 mm** (No. 4) sieve and retained on the **0.075 mm** (No. 200) sieve is fine aggregate. The portion passing the **0.075 mm** (No. 200) sieve is defined as mineral filler. Submit sufficient materials to produce **90 kg** of blended mixture for mix design verification. Submit all aggregate test results and samples to the Government at least 14 days prior to start of construction. Aggregate tests can be no older than 6 months prior to contract award.

2.3.1 Coarse Aggregate

NOTE: The requirement for sulfate soundness (requirement b., below) may be deleted in climates where freeze-thaw does not occur. However, in those areas where freeze-thaw does not occur, keep requirement b. if experience has shown that this test separates good performing aggregates from bad performing aggregates. Retain this requirement for all Navy projects.

It is recommended that percentage of Wear (ASTM C131/C131M) not exceed 40. Aggregates with a higher percentage of wear may be specified, provided a satisfactory record under similar conditions of service and exposure has been demonstrated.

Provide coarse aggregate consisting of sound, tough, durable particles, free from films of material that would prevent thorough coating and bonding with the asphalt material and free from organic matter and other deleterious substances. Provide coarse aggregate particles meeting the following requirements:

- a. The percentage of loss not greater than 40 percent after 500 revolutions when tested in accordance with **ASTM C131/C131M** or **KS F 2508**.
- b. The sodium sulfate soundness loss not exceeding 12 percent, or the magnesium sulfate soundness loss not exceeding 18 percent after five cycles when tested in accordance with **ASTM C88** or **KS F 2507**.
- c. At least 75 percent by weight of coarse aggregate contain at least two or more fractured faces when tested in accordance with **ASTM D5821** with fractured faces produced by crushing.

- d. The particle shape essentially cubical and the aggregate containing not more than 5 percent, by weight, of flat particles, elongated particles, or flat and elongated particles (5:1 ratio of maximum to minimum) when tested in accordance with [ASTM D4791](#) Method A or [KS F 2575](#).
- e. Slag consisting of air-cooled, blast furnace slag, with a compacted weight of not less than 1200 kg per cubic meter when tested in accordance with [ASTM C29/C29M](#) or [KS F 2505](#).
- f. Clay lumps and friable particles not exceeding 0.3 percent, by weight, when tested in accordance with [ASTM C142/C142M](#).

2.3.2 Fine Aggregate

NOTE: Set the lower limit for uncompact void content (requirement c., below) at 45 for fine aggregate angularity unless local experiences indicate that a lower value can be used. There are some aggregates which have a good performance record and have an uncompact void content less than 45. In no case set the limit at less than 43.

Provide fine aggregate consisting of clean, sound, tough, durable particles. Provide aggregate particles that are free from coatings of clay, silt, or any objectionable material, contain no clay balls, and meet the following requirements:

- a. Quantity of natural sand (noncrushed material) added to the aggregate blend not exceeding 15 percent by weight of total aggregate.
- b. Individual fine aggregate sources with a sand equivalent value greater than 45 when tested in accordance with [ASTM D2419](#) or [KS F 2340](#).
- c. Fine aggregate portion of the blended aggregate with an uncompact void content greater than 45.0 percent when tested in accordance with [ASTM C1252](#) Method A or [KS F 2384](#).
- d. Clay lumps and friable particles not exceeding 0.3 percent, by weight, when tested in accordance with [ASTM C142/C142M](#).

2.3.3 Mineral Filler

Provide mineral filler consisting of a nonplastic material meeting the requirements of [ASTM D242/D242M](#) or [KS F 3501](#).

2.3.4 Aggregate Gradation

NOTE: Delete from Table 7, the gradations that will not be used as a part of this project.

Limit use of gradation 1 to intermediate courses. Gradation 2 is suitable for intermediate and surface courses. Limit gradation 3 to shoulders and leveling courses. Do not use gradation 1 for surface courses.

Generally, the layer thickness for gradation No. 1 would be at least 57 mm, the thickness for gradation No. 2 would be at least 37.5 mm, and thickness for gradation No. 3 would be at least 25 mm. The preferred thickness of the surface layer is 50 mm. The surface layer should not be less than 37 mm. The thickness of the underlying layers can be up to 75 mm depending on the total designed thickness of the asphalt mixture.

Provide a combined aggregate gradation that conforms to gradations specified in Table 7, when tested in accordance with ASTM C136/C136M or KS F 2502 and ASTM C117 or KS F 2309, and does not vary from the low limit on one sieve to the high limit on the adjacent sieve or vice versa, but grades uniformly from coarse to fine. Provide a JMF within the specification limits; however, the gradation can exceed the limits when the allowable deviation from the JMF shown in Tables 10 and 11 are applied.

Table 7			
Aggregate Gradations			
	Gradation 1	Gradation 2	Gradation 3
Sieve Size, mm	Percent Passing by Mass	Percent Passing by Mass	Percent Passing by Mass
25.0	100	---	---
19.0	90-100	100	---
12.5	68-88	90-100	100
9.5	60-82	69-89	90-100
4.75	45-67	53-73	58-78
2.36	32-54	38-60	40-60
1.18	22-44	26-48	28-48
0.60	15-35	18-38	18-38
0.30	9-25	11-27	11-27
0.15	6-18	6-18	6-18
0.075	3-6	3-6	3-6

2.4 ASPHALT BINDER

NOTE: Specify Performance Graded (PG) asphalt binders wherever available. Consider using the same grade PG binder used by the state highway department

in the area as the base grade for the project (for example, the grade typically specified in that specific location for dense graded mixes on highways with design ESALS less than 10 million). Do not use grades with a low temperature higher than PG XX-22 (i.e. PG XX-16, PG XX-10).

Select PG 64-22 for normal area and PG 76-22 for heavy duty area, respectively in the local projects.

Typically, rutting is not a problem on airport pavements. However, at airports with a history of stacking on end of runways and taxiway areas, rutting has accrued due to the slow speed of loading on the pavement. If there has been rutting on the project or it is anticipated that stacking may accrue during the design life of the project, then apply the following grade "bumping" for the top 125 mm of paving in the end of runway and taxiway areas: for aircraft tire pressure between 0.7 and 1.4 MPa, increase the high temperature one grade; for aircraft tire pressure greater than 1.4 MPa, increase the high temperature two grades.

For Navy projects, a high temperature increase of two grades is required. Each grade adjustment is 6 degrees C. Polymer Modified Asphalt, PMA, has shown to perform very well in these areas.

The low temperature grade should remain the same. The Engineer may lower the low temperature grade to comply with the recommendations of the FHWA's software program "LTPPBIND", if it is believed to be appropriate.

Retain bracketed verification testing text for runway, taxiway, and apron projects.

For asphalt binders that are anticipated to be polymer modified, select the bracketed text requiring PG Plus testing. If designers are unaware of acceptable elastic recovery, use a minimum percentage of 75.

Provide asphalt binder that conforms to ASTM D6373 for Performance Grade (PG) [64-22] [76-22] or KS F 2389 Performance Grade (PG) [64-22] [76-22]. Provide test data indicating grade certification by the supplier at the time of delivery of each load to the mix plant. Submit copies of these certifications to the Government. The supplier is defined as the last source of any modification to the binder. The Government may sample and test the binder at the mix plant at any time before or during mix production. Obtain samples for this verification testing in accordance with ASTM D140/D140M and in the presence of the Government. Provide these samples to the Government for the verification testing, which will be performed at the Government's expense. Submit 20 L sample of the asphalt binder specified for mix design verification and approval not less than 14 days before start of the test section.

2.5 MIX DESIGN

NOTE: Use 75 blow Marshall hand-held hammer compaction or 75 gyration Superpave gyratory compaction for all pavements designed for tire pressures of 690 kPa or higher.

Use 50 Blow Marshall hand-held hammer compaction or 50 gyration Superpave gyratory compaction for all shoulder pavements and pavements designed for tire pressures less than 690 kPa.

For Marshall mixes, delete the column in Table 8 which does not apply, unless the project includes both 75 Blow and 50 Blow mixes.

Select the appropriate gradation and VMA requirements in Table 9 to be consistent with the gradation chosen in Table 7. Delete the other two rows in Table 9 unless using multiple gradations.

In areas exposed to frequent freeze/thaw, require freeze/thaw conditioning.

Develop the mix design and provide results of the Job Mix formula (JMF) and aggregates testing performed no earlier than 6 months prior to contract award. Provide asphalt mixture composed of well-graded aggregate, mineral filler if required, and asphalt material. Provide aggregate fractions sized, handled in separate size groups, and combined in such proportions that the resulting mixture meets the grading requirements of Table 7. Do not produce asphalt pavement for payment until a JMF has been approved. Design the asphalt mixture using hand-held (manual) Marshall hammer procedures contained in AI MS-2 and the criteria shown in Table 8. Mechanical hammers are not permitted during JMF development. Prepare samples at various asphalt contents and compacted in accordance with ASTM D6926. Use laboratory compaction temperatures for Polymer Modified Asphalts as recommended by the asphalt binder supplier. For tensile strength ratio (TSR) testing, adjust the compactive effort, as required, to provide specimens with an air void content of 7 plus or minus 1 percent. Use freeze/thaw conditioning in lieu of moisture conditioning per Note 6 of ASTM D4867/D4867M or KS F 2352. If freeze/thaw conditioning is used, include that fact on the report. If the Tensile Strength Ratio (TSR) of the composite mixture, as determined by ASTM D4867/D4867M or KS F 2352 is less than 75, reject the aggregates or treat the asphalt mixture with an anti-stripping agent. Add a sufficient amount of anti-stripping agent to produce a TSR of not less than 75. If an antistrip agent is required, provide it at no additional cost to the Government. Provide sufficient materials to produce 90 kg of blended mixture to the Government for verification of mix design at least 14 days prior to construction of test section.

2.5.1 JMF Requirements

Submit the proposed JMF in writing, for approval, at least 14 days prior to the start of the test section, including as a minimum:

- a. Percent passing each sieve size.
- b. Optimum asphalt content.
- c. Percent of each aggregate and mineral filler to be used.
- d. Asphalt viscosity grade, penetration grade, or performance grade and additional test requirements as specified in paragraph ASPHALT BINDER.
- e. Number of blows of hammer per side of molded specimen.
- f. Laboratory mixing and compaction temperatures.
- g. Supplier-recommended field mixing and compaction temperatures.
- h. Percentage and properties (asphalt content aggregate gradation, and aggregate properties) of RAP in accordance with paragraph RECYCLED ASPHALT PAVEMENT, if RAP is used.
- i. Temperature-viscosity relationship of the asphalt binder.
- j. Plot of the combined gradation on the 0.45 power gradation chart, stating the nominal maximum size.
- k. Graphical plots and summary tabulation of stability, flow, air voids, voids in the mineral aggregate, and unit weight versus asphalt content as shown in AI MS-2. Include summary tabulation that includes individual specimen data for each specimen tested.
- l. Specific gravity and absorption of each aggregate.
- m. Percent natural sand.
- n. Percent particles with two or more fractured faces (in coarse aggregate).
- o. Fine aggregate angularity.
- p. Percent flat or elongated particles (in coarse aggregate).
- q. Tensile Strength Ratio and wet/dry specimen test results.
- r. Type and amount of antistrip agent (if required).
- s. List of all modifiers.
- t. Percentage and properties (asphalt content aggregate gradation, and aggregate properties) of RAP in accordance with paragraph RECLAIMED ASPHALT PAVEMENT, if RAP is used.
- u. Date the JMF was developed. Mix designs that are not dated or which are from a prior construction season may not be accepted.

Table 8		
Marshall Design Criteria		
Test Property	75 Blow Mix	50 Blow Mix
Stability, N minimum	9560 ⁽¹⁾	6000 ⁽¹⁾
Flow, 0.25 mm	8-16 ⁽²⁾	8-18 ⁽²⁾
Air voids, percent	4 ⁽⁴⁾	4 ⁽⁴⁾
Percent Voids in mineral aggregate (minimum)	See Table 9	See Table 9
Dust Proportion ⁽³⁾	0.8-1.2	0.8-1.2
TSR, minimum percent	75	75
TSR Conditioned Strength (minimum kPa)	415	415
(1) This is a minimum requirement. Provide significantly higher average during construction to ensure compliance with the specifications.		
(2) The flow requirement is not applicable for Polymer Modified Asphalts		
(3) Dust Proportion is calculated as the aggregate content, expressed as a percent of mass, passing the 0.075 mm (No. 200) sieve, divided by the effective asphalt content, in percent of total mass of the mixture.		
(4) Select the JMF asphalt content corresponding to an air void content of 4 percent. Verify the other properties of Table 8 meet the specification requirements at this asphalt content.		

Table 9	
Minimum Percent Voids in Mineral Aggregate (VMA) ⁽¹⁾	
Aggregate (See Table 7)	Minimum VMA, percent
Gradation 1	13.0
Gradation 2	14.0
Gradation 3	15.0
(1) Calculate VMA in accordance with AI MS-2, based on ASTM C127 or KS F 2503 and ASTM C128 or KS F 2504 bulk specific gravity for the aggregate.	

2.5.2 Adjustments to JMF

The JMF for each mixture is in effect until a new formula is approved in writing by the Government. Should a change in sources of any materials be made, perform a new mix design and a new JMF approved before the new material is used. Make minor adjustments within the specification limits

to the JMF to optimize mix volumetric properties. Adjustments to the original JMF are limited to plus or minus 4 percent on the 4.75 mm (No. 4) and coarser sieves; plus or minus 3 percent on the 2.36 mm (No. 8) to 0.30 mm (No. 50) sieves; and plus or minus 1 percent on the 0.15 mm (No. 100) sieve. Adjustments to the JMF are limited to plus or minus 1.0 percent on the 0.075 mm (No. 200) sieve. Asphalt content adjustments are limited to plus or minus 0.40 from the original JMF. If adjustments are needed that exceed these limits, develop a new mix design.

2.6 RECLAIMED ASPHALT PAVEMENT

NOTE: Do not use Reclaimed Asphalt Pavement (RAP) for surface mixes, except on shoulders. It can be used very effectively in lower layers, or for shoulders. Limit the amount of RAP so the asphalt binder from the RAP does not exceed 20 percent of the total asphalt content.

Select first bracketed text when RAP is not used and delete the following two paragraphs. Select second bracketed text when RAP will be used for shoulders or lower layers (non-surface) and keep the following two paragraphs.

Reclaimed asphalt is not allowed for the project.

2.6.1 RAP Mix

Do not make adjustments to the virgin binder selection for 0-20 percent recycled binder content.

2.7 RECYCLED ASPHALT SHINGLES

NOTE: Recycled asphalt shingles (RAS) usually is available as pre-consumer (manufacturer waste) or post consumer (tear-off) products. Due to the extreme stiffness of the binder in these products, do not allow on airfield pavements. Contact the cognizant representatives of the Corps of Engineers Transportation Systems Center (TSMCX), the Air Force Civil Engineer Center (AFCEC) pavement subject matter expert (SME), or the Naval Facilities Engineering Systems Command (NAVFAC) engineer for further guidance if RAS is being further considered.

Recycled asphalt shingles (RAS) is not allowed for the project.

PART 3 EXECUTION

3.1 CONTRACTOR QUALITY CONTROL

NOTE: The Contractor may be able to meet the specified quality control requirements with in-house capability or may have to use the independent

**commercial laboratory to provide the required
quality control testing.**

3.1.1 General Quality Control Requirements

Submit the Pavement Quality Control Plan. The Quality Control Plan is specific to this specification and supplements the overall Quality Control Plan required by Section 01 45 00. Do not produce hot-mix asphalt pavement for payment until the quality control plan has been approved. In the quality control plan, address all elements which affect the quality of the pavement including, but not limited to:

- a. Mix Design and unique JMF identification code
- b. Aggregate Grading
- c. Quality of Materials
- d. Stockpile Management and procedures to prevent contamination
- e. Proportioning
- f. Mixing and Transportation
- g. Mixture Volumetrics
- h. Moisture Content of Mixtures
- i. Placing and Finishing
- j. Joints
- k. Compaction, including Asphalt Pavement-Portland Cement Concrete joints
- l. Surface Smoothness
- m. Truck bed release agent
- n. Correlation of mechanical hammer to hand-held (manual) hammer. Determine the number of blows of the mechanical hammer required to provide the same density of the JMF as provided by the hand-held (manual) hammer. Use the average of three specimens per trial blow application.

3.1.2 Testing Laboratory

Provide a fully equipped asphalt laboratory located at the plant or job site that is equipped with heating and air conditioning units to maintain a temperature of 24 plus or minus 2.3 degrees C. Provide laboratory facilities that are kept clean and all equipment maintained in proper working condition. Provide the Government with unrestricted access to inspect the laboratory facility, to witness quality control activities, and to perform any check testing desired. The Government will advise in writing of any noted deficiencies concerning the laboratory facility, equipment, supplies, or testing personnel and procedures. When the deficiencies are serious enough to adversely affect test results, immediately suspend the incorporation of the materials into the work. Incorporation of the materials into the work will not be permitted to

resume until the deficiencies are corrected.

3.1.3 Quality Control Testing

Perform all quality control tests applicable to these specifications and as set forth in the Quality Control Program. The quality control (QC) testing is separate and distinct from the acceptance testing in paragraph ACCEPTANCE. Use in-house capabilities or the independent commercial laboratory for quality control testing. Required elements of the testing program include, but are not limited to, tests for the control of asphalt content, aggregate gradation, temperatures, aggregate moisture, moisture in the asphalt mixture, laboratory air voids, [stability](#), [flow](#), in-place density, grade and smoothness. Develop a Quality Control Testing Plan as part of the Quality Control Program.

3.1.3.1 Asphalt Content

Determine asphalt content a minimum of twice per lot (a lot is defined in paragraph PAVEMENT LOTS) by one of the following methods: extraction method in accordance with [ASTM D2172/D2172M](#), Method A or B or [KS F 2354](#), method A or B, the ignition method in accordance with [ASTM D6307](#), or the nuclear method in accordance with [ASTM D4125/D4125M](#), provided each method is calibrated for the specific mix being used. For the extraction method, determine the weight of ash, as described in [ASTM D2172/D2172M](#) or [KS F 2354](#), as part of the first extraction test performed at the beginning of plant production; and as part of every tenth extraction test performed thereafter, for the duration of plant production. Use the last weight of ash value in the calculation of the asphalt content for the mixture. The asphalt content for the lot will be determined by averaging the test results.

3.1.3.2 Aggregate Properties

Determine aggregate gradations a minimum of twice per lot (a lot is defined in paragraph PAVEMENT LOTS) from mechanical analysis of recovered aggregate in accordance with [ASTM D5444](#), [ASTM C136/C136M](#) or [KS F 2502](#), and [ASTM C117](#) or [KS F 2309](#). Determine the specific gravity of each aggregate size grouping for each [18,000 metric tons](#) in accordance with [ASTM C127](#) or [KS F 2503](#); or [ASTM C128](#) or [KS F 2504](#). Determine fractured faces for gravel sources for each [18,000 metric tons](#) in accordance with [ASTM D5821](#). Determine the uncompacted void content of fine aggregate (including manufactured sand and blending aggregate) for each [18,000 metric tons](#) in accordance with [ASTM C1252](#) Method A or [KS F 2384](#).

3.1.3.3 Temperatures

Check temperatures at least four times per lot, at necessary locations, to determine the temperature at the dryer, the asphalt binder in the storage tank, the asphalt mixture at the plant, and the asphalt mixture at the job site.

3.1.3.4 Moisture Content of Aggregate

Determine the moisture content of aggregate used for production a minimum of once per lot in accordance with [ASTM C566](#).

3.1.3.5 Moisture Content of Mixture

Determine the moisture content of the mixture at least once per lot in

accordance with AASHTO T 329 or KS F 2372.

3.1.3.6 Laboratory Air Voids, TMD, VMA, Marshall Stability and Flow

Obtain mixture samples at least four times per lot and compacted into specimens, using [50] [75] blows per side with the Marshall hand-held (manual) hammer as described in ASTM D6926. The mechanical Marshall hammer can be used only after JMF development and after correlation from hand-held (manual) Marshall hammer to mechanical Marshall hammer per guidance in AI MS-2. After compaction, measure the bulk density of laboratory compacted specimens in accordance with ASTM D2726/D2726M or KS F 2353. Determine the laboratory air voids from the set (three laboratory compacted specimens) for each sample in accordance with ASTM D3203/D3203M or KS F 2364. Also calculate the VMA of each specimen in accordance with AI MS-2 based on ASTM C127 or KS F 2503 and ASTM C128 or KS F 2504 bulk specific gravity for the aggregate, as well as the Marshall stability and flow, as described in ASTM D6927. Provide VMA within the limits of Table 9.

3.1.3.7 In-Place Density

Conduct any necessary testing to ensure the specified density is achieved. A nuclear gauge or other non-destructive testing device may be used to monitor pavement density for Contractor Quality Control purposes only.

3.1.3.8 Grade and Smoothness

Conduct the necessary checks to ensure the grade and smoothness requirements are met in accordance with paragraph ACCEPTANCE.

3.1.3.9 Additional Testing

Perform any additional testing, deemed necessary to control the process.

3.1.3.10 QC Monitoring

Submit all QC test results to the Government on a daily basis as the tests are performed. The Government reserves the right to monitor any of the Contractor's quality control testing and to perform duplicate testing as a check to the Contractor's quality control testing.

3.1.4 Sampling

When directed by the Government, sample and test any material which appears inconsistent with similar material being produced, unless such material is voluntarily removed and replaced or deficiencies corrected. Perform all sampling in accordance with standard procedures specified.

3.1.5 Control Charts

For process control, establish and maintain linear control charts on both individual samples and the running average of last four samples for the parameters listed in Table 10, as a minimum. Post the control charts as directed by the Government and maintain current at all times. Identify the following on the control charts, the project number, the test parameter being plotted, the individual sample numbers, the Action and Suspension Limits listed in Table 10 applicable to the test parameter being plotted, and the test results. Also show target values (JMF) on the control charts

as indicators of central tendency for the cumulative percent passing, asphalt content, and laboratory air voids parameters. When the test results exceed either applicable Action Limit, take immediate steps to bring the process back in control. When the test results exceed either applicable Suspension Limit, halt production until the problem is solved. When the Suspension Limit is exceeded for individual values or running average values, the Government has the option to require removal and replacement of the material represented by the samples or to leave in place and base acceptance on mixture volumetric properties and in place density. Use the control charts as part of the process control system for identifying trends so that potential problems can be corrected before they occur. Make decisions concerning mix modifications based on analysis of the results provided in the control charts. In the Quality Control Plan, indicate the appropriate action to be taken to bring the process into control when certain parameters exceed their Action Limits.

Table 10				
Action and Suspension Limits for the Parameters to be Plotted on Individual and Running				
	Individual Samples		Running Average of Last Four Samples	
Parameter to be Plotted	Action Limit	Suspension Limit	Action Limit	Suspension Limit
4.75 mm (No. 4) sieve, Cumulative Percent Passing, deviation from JMF target; plus or minus values	6	8	4	5
0.6 mm (No. 30) sieve, Cumulative Percent Passing, deviation from JMF target; plus or minus values	4	6	3	4
0.075 mm (No. 200) sieve, Cumulative Percent Passing, deviation from JMF target; plus or minus values	1.4	2.0	1.1	1.5
Asphalt content, percent deviation from JMF target; plus or minus value	0.4	0.5	0.2	0.3
Laboratory Air Voids, percent deviation from JMF target value	No specific action and suspension limits set since this parameter is used to determine percent payment			
In-place Mat Density, percent	No specific action and suspension limits set since this parameter is used to determine percent payment			
In-place Joint Density, percent	No specific action and suspension limits set since this parameter is used to determine percent payment			
VMA, percent deviation from JMF target				
Gradation 1, 2 & 3	-0.5	-1.0	-0.25	-0.5
P _{0.075} /P _{be} Ratio, deviation from 1.0; plus or minus values	0.7	0.8	0.3	0.4

Table 10 cont'd				
Action and Suspension Limits for the Parameters to be Plotted on Individual and Running Average Control Charts - Marshall Compaction				
Stability, N (minimum)				
75 blow JMF	7830	7290	9560	9030
50 blow JMF	4230	3690	6000	5470
Flow, 0.25 mm				
75 blow JMF	8 min.	7 min.	9 min.	8 min.
	16 max.	17 max.	15 max.	16 max.
50 blow JMF	8 min.	7 min.	9 min.	8 min.
	18 max.	19 max.	17 max.	18 max.

3.2 Government Quality Assurance (QA)

Notify the Contracting Officer in writing to allocate Quality Assurance tests which will be performed by FED Geotechnical and Environmental Engineering Branch at a minimum ten percent of the Quality Control tests. The Government Quality Assurance (QA) program for this project is separate and distinct from the Contractor's Quality Control (QC) program specified herein.

Keep records and logs of QA test [notification](#). E-mails may be used as the records.

All contractor quality control testing laboratories performing acceptance testing in Korea must require USACE validation every year for all laboratories such as parent laboratory, on-site laboratory, commercial laboratory and plant laboratory by Material Testing Laboratory(MTL), Geotechnical and Environmental Engineering Branch, Far East District who always maintains inspection capability of quality control testing laboratories through periodical inspection by Material Testing Center(MTC), Engineer Research and Development Center (ERDC), USACE. Validation on all laboratories must be required to remain current throughout the duration of the paving project.

Quality control testing laboratory inspections must be planned by the Contractor through QC Test Plan submittal that must contain which laboratory will conduct each quality control testing; and initiated by the Contractor's request through QC Testing List for laboratory inspection which determines which laboratory will be inspected and the scope of laboratory inspection of this project. The first inspection of the laboratories will be at the expense of the Government and any subsequent inspections required because of failure of the first inspection must be at the expense of the Contractor. Such cost must be deducted from the total amount due the Contractor.

3.3 PREPARATION OF ASPHALT BINDER MATERIAL

Heat the asphalt binder material while avoiding local overheating and providing a continuous supply of the asphalt material to the mixer at a uniform temperature. Maintain the temperature of unmodified asphalts to no more than 160 degrees C when added to the aggregates. The temperature of modified asphalts is not to exceed 175 degrees C.

3.4 PREPARATION OF MINERAL AGGREGATE

Heat and dry the aggregate for the mixture prior to mixing. No damage to the aggregates due to the maximum temperature and rate of heating used is allowed. Maintain the temperature no lower than is required to obtain complete coating and uniform distribution on the aggregate particles and to provide a mixture of satisfactory workability.

3.5 PREPARATION OF ASPHALT MIXTURE

Weigh or meter the aggregates and the asphalt binder and introduce into the mixer in the amount specified by the JMF. Limit the temperature of the asphalt mixture to 175 degrees C when the asphalt binder is added. Mix the combined materials until the aggregate obtains a thorough and uniform coating of asphalt binder (testing in accordance with ASTM D2489/D2489M or KS F 2360 may be required by the Contracting Officer) and is thoroughly distributed throughout the mixture. The moisture content of all asphalt mixture upon discharge from the plant is not to exceed 0.5 percent by total weight of mixture as measured by AASHTO T 329 or KS F 2372.

3.6 PREPARATION OF THE UNDERLYING SURFACE

NOTE: If the underlying surface to be paved is an unbound granular layer, apply a prime coat, especially if this layer will be exposed to weather for an extended period of time prior to covering with an asphalt mixture. Benefits derived from a prime coat include an additional weatherproofing of the base, improving the bond between the base and asphalt layer, and preventing the base from shifting under construction equipment. If the prime coat requirement is not a separate pay item and is waived from this contract, make an adjustment to the contract price. Environmental laws in certain states may not allow prime coats to be applied.

If the underlying surface to be paved is an existing asphalt or concrete layer, use a tack coat to ensure an adequate bond between layers.

Tack and prime coat requirements will need to be covered in the contract documents.

Immediately before placing asphalt pavement, clean the underlying course of dust and debris. Apply a prime coat or tack coat in accordance with Section 32 12 13 BITUMINOUS TACK AND PRIME COATS.

3.7 TEST SECTION

Prior to full production, place a test section for each JMF used. Construct a test section 150 m long and two paver passes wide with a longitudinal cold joint. Do not place the second lane of test section until the temperature of pavement edge is less than 80 degrees C. Construct the test section with the same depth as the course which it represents. Ensure the underlying grade or pavement structure upon which the test section is to be constructed is the same or very similar to the underlying layer for the project. Use the same equipment in construction of the test section as on the remainder of the course represented by the test section. Construct the test section as part of the project pavement as approved by the Government.

3.7.1 Sampling and Testing for Test Section

NOTE: Table 11 applies only to the test section.
The limits in Tables 1, 3, and 10, apply to a number
of tests run from a lot. This is why the limits
listed in Table 11 are different from those listed
in Tables 1, 3 and 10.

Select the appropriate stability and flow value to
match the laboratory compactive effort (50 or 75
blows).

Obtain one representative sample from random trucks at the plant, compact triplicate specimens, and test for stability, flow, and laboratory air voids. Test a portion of the same sample for theoretical maximum density (TMD), aggregate gradation and asphalt content. Test an additional portion of the sample to determine the TSR. Adjust the compactive effort as required to provide TSR specimens with an air void content of 7 plus or minus 1 percent. Obtain four randomly selected cores from the finished pavement mat, and four from the longitudinal joint, and test for density. Perform random sampling in accordance with procedures contained in ASTM D3665. Construction may continue provided the test results are within the tolerances or exceed the minimum values shown in Table 11. If all test results meet the specified requirements, the test section may remain as part of the project pavement. If test results exceed the tolerances shown, remove and replace the test section and construct another test section at no additional cost to the Government.

Table 11	
Test Section Requirements for Material and Mixture Properties	
Property	Specification Limit
Aggregate Gradation-Percent Passing (Individual Test Result)	
4.75 mm (No. 4) and larger	JMF plus or minus 8
2.36 (No. 8), 1.18 (No. 16), 0.60 (No. 30), 0.30 (No. 60) and 0.15 (No. 100)	JMF plus or minus 6
0.15 (No. 100) and 0.075 mm (No. 200)	JMF plus or minus 2.0
Asphalt Content, Percent (Individual Test Result)	JMF plus or minus 0.5
Laboratory Air Voids, Percent (Average of 3 specimens)	JMF plus or minus 1.0

Table 11	
Test Section Requirements for Material and Mixture Properties	
Property	Specification Limit
VMA, Percent (Average of 3 specimens)	See Table 9
Tensile Strength Ratio (TSR) (At 7 percent plus/minus 1 percent air void content)	75 percent minimum
Conditioned Strength	415 kPa minimum
Mat Density, Percent of TMD (Average of 4 Random Cores)	92.0 - 96.0
Joint Density, Percent of TMD (Average of 4 Random Cores)	90.5 minimum
Table 11 cont'd	
Test Section Requirements for Material and Mixture Properties Marshall Compaction	
Stability, (Average of 3 specimens)	[9560 N minimum for 75-blow][6000 N minimum for 50-blow]
Flow, 0.25 mm (Average of 3 specimens)	[8 - 16 for 75-blow] [8 - 18 for 50-blow]

3.7.2 Additional Test Sections

If the initial test section proves to be unacceptable, make the necessary adjustments to the JMF, plant operation, placing procedures, and rolling procedures before beginning construction of a second test section. Construct and evaluate additional test sections, as required, for conformance to the specifications. Full production paving is not allowed to begin until an acceptable test section has been constructed and accepted.

3.8 TRANSPORTING AND PLACING

3.8.1 Transporting

Transport asphalt mixture from the mixing plant to the site in clean, tight vehicles. Schedule deliveries so that placing and compacting of mixture is uniform with minimum stopping and starting of the paver. Provide adequate artificial lighting for night placements. Hauling over freshly placed material is not permitted until the material has been compacted as specified, and allowed to cool to 60 degrees C.

3.8.2 Placing

Place the mix in lifts of adequate thickness and compacted at a temperature suitable for obtaining density, surface smoothness, and other specified requirements. Place the mixture to the full width by an asphalt paver; strike off in a uniform layer of such depth that, when the work is complete, the required thickness conforms to the grade and contour indicated. Do not broadcast waste mixture onto the mat or recycle it into the paver hopper. Collect waste mixture and dispose off site. Regulate

the speed of the paver to eliminate pulling and tearing of the asphalt mat. Begin placement of the mixture along the centerline of a crowned section or on the high side of areas with a one-way slope. Place the mixture in consecutive adjacent strips having a minimum width of 3 m. Offset the longitudinal joint in one course from the longitudinal joint in the course immediately below by at least 300 mm; however, locate the joint in the surface course at the centerline of the pavement. Offset transverse joints in one course by at least 3 m from transverse joints in the previous course. Offset transverse joints in adjacent lanes a minimum of 3 m. On isolated areas where irregularities or unavoidable obstacles make the use of mechanical spreading and finishing equipment impractical, the mixture may be spread and luted by hand tools. Construct the free edge of shoulder pavements following a guide (e.g. plumb-bob, stringline, etc.) to prevent various widths of the asphalt shoulder. Contractor may elect to cut-back the asphalt edge to maintain consistent shoulder dimensions shown on the plans.

3.9 COMPACTION OF MIXTURE

3.9.1 General

- a. After placing, thoroughly and uniformly compact the mixture by rolling. Compact the surface as soon as possible without causing displacement, cracking or shoving. Determine the sequence of rolling operations and the type of rollers used, except as specified in paragraph ASPHALT PAVEMENT-PORTLAND CEMENT CONCRETE JOINTS. Maintain the speed of the roller, at all times, sufficiently slow to avoid displacement of the asphalt mixture and be effective in compaction. Correct at once any displacement occurring as a result of reversing the direction of the roller, or from any other cause.
- b. Furnish sufficient rollers to handle the output of the plant. Continue rolling until the surface is of uniform texture, true to grade and cross section, and the required field density is obtained. To prevent adhesion of the mixture to the roller, keep the drums properly moistened, but excessive water is not permitted. In areas not accessible to the roller, thoroughly compact the mixture with hand tampers. Remove the full depth of any mixture that becomes loose and broken, mixed with dirt, contains check-cracking, or is in any way defective, replace with fresh asphalt mixture and immediately compact to conform to the surrounding area. Perform this work at no expense to the Government. Skin patching is not allowed.

3.9.2 Segregation

The Government can sample and test any material that looks deficient. When the in-place material appears to be segregated, the Government has the option to sample the material and have it tested and compared to the aggregate gradation, asphalt content, and in-place density requirements in Table 11. If the material fails to meet these specification requirements, remove and replace the extent of the segregated material the full depth of the layer of asphalt mixture at no additional cost to the Government. When segregation occurs in the mat, take appropriate action to correct the process so that additional segregation does not occur.

3.10 JOINTS

Construct joints to ensure a continuous bond between the courses and to obtain the required density. Provide all joints with the same texture as

other sections of the course and meet the requirements for smoothness and grade.

3.10.1 Transverse Joints

Do not pass the roller over the unprotected end of the freshly laid mixture, except when necessary to form a transverse joint. When necessary to form a transverse joint, construct by means of placing a bulkhead or by tapering the course. Utilize a dry saw cut on the transverse joint full depth and width on a straight line to expose a vertical face prior to placing the adjacent lane. Neither cutting equipment that uses water as a cooling or cutting agent nor milling equipment is permitted. Remove the cutback material and cutting debris from the project. Provide a tack coat in accordance with Section 32 12 13 BITUMINOUS TACK AND PRIME COATS to all contact surfaces before placing any fresh mixture against the joint.

3.10.2 Longitudinal Joints

Cut back longitudinal joints which are irregular, damaged, uncompacted, cold (less than 80 degrees C at the time of placing the adjacent lane), or otherwise defective, a minimum of 75 mm and a maximum of 150 mm from the top edge of the lift with a cutting wheel to expose a clean, sound, near vertical surface for the full depth of the course. Remove all cutback material from the project. Neither cutting equipment that uses water as a cooling or cutting agent nor milling equipment is permitted. Remove the cutback material and cutting debris from the project. Provide tack coat in accordance with Section 32 12 13 BITUMINOUS TACK AND PRIME COATS to all contact surfaces prior to placing any fresh mixture against the joint.

3.10.3 Echelon Paving

If echelon paving is accomplished to minimize longitudinal cold joints, visually inspect the interface between the two paving lanes to ensure that the interface is not segregated or appears to be visually different from other sections of the course. If visual inspection identifies quality concerns, extract 1 randomly selected cores per subplot centered over the interface between the two paving lanes being placed. The requirements for density at the interface between the two echelon paved lanes are the same as that for the joint density specified in paragraph MAT AND JOINT DENSITIES.

3.10.4 Asphalt Pavement-Portland Cement Concrete Joints

Joints between asphalt pavement and Portland Cement Concrete (PCC) require specific construction procedures for the asphalt pavement. The following criteria are applicable to the first 3 m or paver width of asphalt pavement adjacent to the PCC.

- a. For all lifts, place the asphalt pavement side of the joint in a direction parallel to the joint.
- b. For non-surface lifts (e.g. base or intermediate lifts), compact the mixture per paragraph MAT AND JOINT DENSITIES.
- b. For the surface lift place the asphalt pavement side sufficiently high so that when fully compacted the asphalt pavement is greater than 3 mm but less than 6 mm higher than the PCC side of the joint.
- c. For the surface lift, compact with steel wheel rollers and at least

one rubber tire roller. Compact with a rubber tire roller that weights at least 18 metric tons with tires inflated to at least 620 kPa. Avoid spalling the PCC during placement and compaction of the asphalt pavement. Operate steel wheel rollers in a way that prevents spalling the PCC. Repair any damage to PCC edges or joints as directed by the Government. If damage to the PCC joint or panel edge exceeds a total of 1 m, remove and replace the PCC panel at no additional expense to the Government.

- d. For the surface lift, after compaction is finished, diamond grind a minimum width of 1 m of the asphalt pavement so that the asphalt pavement side is less than 3 mm higher than the PCC side. Perform diamond grinding in accordance with subparagraph DIAMOND GRINDING above. The asphalt pavement immediately adjacent to the joint is not allowed to be lower than the PCC after the grinding operation. Transition the grinding into the asphalt pavement in a way that ensures good smoothness and provides drainage of water. The joint and adjacent materials when completed is required to meet all of the requirements for grade and smoothness. Measure smoothness across the asphalt pavement-PCC joint using a 4 m straightedge. The acceptable tolerance is 3 mm.
- e. For all lifts, consider the asphalt pavement next to the PCC as a separate weighted pay factor associated with the lot being placed for evaluation. Lots are based on individual lifts. Do not commingle cores from different lifts for density evaluation purposes. Take four cores for each lot of material placed adjacent to the asphalt pavement-PCC joint. The size of lot is 3 m wide by the length of the joint being paved. Perform the same computation as displayed in paragraph PAY FACTOR BASED ON IN-PLACE DENSITY above to determine the weighted pay factor. Select the lowest computed pay factor for the lot. Locate the center of each of the four cores 150 mm from the edge of the concrete. Take each core at a random location along the length of the joint. The requirements for joint density, adjacent to the PCC joint, are the same as that for the mat density specified in Table 1. For asphalt pavement-PCC joints at taxiways abutting runways, aprons, or other taxiways, take two additional randomly located cores along each taxiway intersection.
- f. All procedures, including repair of damaged PCC, are required to be in accordance with the approved Quality Control Plan.

-- End of Section --